

VIVO RAISER SDN. BHD. (920807-P)

9 & 10, JLN PKNK 3/7, KAWASAN PERUSAHAAN SUNGAI PETANI 08000 SUNGAI PETANI, KEDAH, MALAYSIA



Phone: 04-4102148 Email: sales@shijiru.com

METHOD STATEMENT FOR TPS MINYAK 338 Grey

1. INTRODUCTION

TPS Minyak 338 Grey is a high quality plaster top coat for internal wall finishes. It can minimize shrinkage crack up to 90% at the same time provides excellent workability.

2. SUBSTRATE EXAMINATION

Before carrying out plastering works, ensure that: -

a. All surfaces must be clean, free from dust, oil or traces of foreign materials that can affects adhesion. Protrusions such as wood peels and nails have to be removed prior to apply plastering top coat finishes.

3. SUBSTRATE PREPARATION

Before carrying out the plastering top coat finishing works, ensure that: -

- a. All surfaces must be clean, free from dust, oil or traces of foreign materials.
- b. Wetting of substrate is recommended if the substrate is too dry before the application of TPS Minyak 338 Grey



VIVO RAISER SDN. BHD. (920807-P)

9 & 10, JLN PKNK 3/7, KAWASAN PERUSAHAAN SUNGAI PETANI 08000 SUNGAI PETANI, KEDAH, MALAYSIA



Phone: 04-4102148 Email: sales@shijiru.com

4. APPLICATION

- a. Mix 20kg of TPS Minyak 338 Grey with 5litres of clean water until a homogeneous paste is achieved. Additional water can be added if required.
- b. A resting time of 3 minutes is recommended for best consistency.
- c. TPS Minyak 338 Grey mortar is applied using a steel trowel or spatula. As good practice, a maximum thickness of 2mm is recommended (2-3 coats).

5. REMARK

- TPS Minyak 338 Grey is suitable for interior use only.
- TPS Minyak 338 Grey should not be applied on painted surfaces.

6. DISCLAIMER

This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is to the best of the company's knowledge and believed accurate and reliable as of the date indicated. However, no representation, warranty or guarantee of any kind, express or implied, is made as to its accuracy, reliability or completeness and we assume no responsibility for any loss, damage or expense, direct or consequential, arising out of use. It is the user's responsibility to satisfy himself as to the suitableness and completeness of such information for his own particular use. Neither Shijiru Sdn Bhd nor any of its parent's companies assumes any liability what so ever for the accuracy or completeness of the information contained herein.